



TEST REPORT

DATE: 03-31-2023

Page 1 of 4

TEST NUMBER: 0295655

| | |
|---------------|-------------|
| CLIENT | Lions Floor |
|---------------|-------------|

| | |
|------------------------------|--|
| TEST METHOD CONDUCTED | ASTM D4060 Standard Test Method for Abrasion Resistance of Organic Coatings by the Taber Abraser |
|------------------------------|--|



| DESCRIPTION OF TEST SAMPLE | |
|----------------------------|-------------------|
| IDENTIFICATION | Comfort Heights |
| COLOR | Country Aura |
| ROLL NUMBER | SKU: LI-CH07 |
| CONSTRUCTION | Laminate Flooring |

GENERAL PRINCIPLE

A test specimen is subjected to the rubbing action of two abrading wheels under controlled conditions of pressure and abrasive action. The abrasion wheels rest on the surface of the specimen which is mounted on a rotating platform. Turning of the platform initiates the abrasive action on the test specimen.

TEST RESULTS

| | |
|-------------------------|-------------|
| ABRASION WHEEL | H-18 |
| LOAD APPLIED | 1,000 Grams |
| NUMBER OF CYCLES | 500 |

| | |
|------------------------|--------------------|
| ORIGINAL WEIGHT | 116.24 Grams |
| FINAL WEIGHT | 116.19 Grams |
| WEIGHT LOSS | 0.05 Grams (0.04%) |
| THICKNESS LOSS | 0.003 Inch |

APPROVED BY: *Gary Osbourn*



This facility is accredited by the National Voluntary Laboratory Accreditation Program for the specific scope of accreditation under Lab Code 100297. This accreditation does not constitute an endorsement, certification, or approval by NIST or any agency of the United States Government for the product tested. This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical or similar products. This report, or the name of Professional Testing Laboratory, Inc. shall not be used under any circumstance in advertising to the general public.





TEST REPORT

DATE: 03-31-2023

Page 2 of 4

TEST NUMBER: 0295655

| | |
|---------------|-------------|
| CLIENT | Lions Floor |
|---------------|-------------|

| | |
|------------------------------|--|
| TEST METHOD CONDUCTED | ASTM D4060 Standard Test Method for Abrasion Resistance of Organic Coatings by the Taber Abraser |
|------------------------------|--|



| DESCRIPTION OF TEST SAMPLE | |
|----------------------------|-------------------|
| IDENTIFICATION | Comfort Heights |
| COLOR | Country Aura |
| ROLL NUMBER | SKU: LI-CH07 |
| CONSTRUCTION | Laminate Flooring |

GENERAL PRINCIPLE

A test specimen is subjected to the rubbing action of two abrading wheels under controlled conditions of pressure and abrasive action. The abrasion wheels rest on the surface of the specimen which is mounted on a rotating platform. Turning of the platform initiates the abrasive action on the test specimen.

TEST RESULTS

| | |
|-------------------------|-------------|
| ABRASION WHEEL | H-18 |
| LOAD APPLIED | 1,000 Grams |
| NUMBER OF CYCLES | 1,000 |

| | |
|------------------------|--------------------|
| ORIGINAL WEIGHT | 116.24 Grams |
| FINAL WEIGHT | 116.16 Grams |
| WEIGHT LOSS | 0.08 Grams (0.07%) |
| THICKNESS LOSS | 0.003 Inch |

APPROVED BY: *Gary Osbourn*



This facility is accredited by the National Voluntary Laboratory Accreditation Program for the specific scope of accreditation under Lab Code 100297. This accreditation does not constitute an endorsement, certification, or approval by NIST or any agency of the United States Government for the product tested. This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical or similar products. This report, or the name of Professional Testing Laboratory, Inc. shall not be used under any circumstance in advertising to the general public.





TEST REPORT

DATE: 03-31-2023

Page 3 of 4

TEST NUMBER: 0295655

| | |
|---------------|-------------|
| CLIENT | Lions Floor |
|---------------|-------------|

| | |
|------------------------------|--|
| TEST METHOD CONDUCTED | ASTM D4060 Standard Test Method for Abrasion Resistance of Organic Coatings by the Taber Abraser |
|------------------------------|--|



| DESCRIPTION OF TEST SAMPLE | |
|----------------------------|-------------------|
| IDENTIFICATION | Comfort Heights |
| COLOR | Country Aura |
| ROLL NUMBER | SKU: LI-CH07 |
| CONSTRUCTION | Laminate Flooring |

GENERAL PRINCIPLE

A test specimen is subjected to the rubbing action of two abrading wheels under controlled conditions of pressure and abrasive action. The abrasion wheels rest on the surface of the specimen which is mounted on a rotating platform. Turning of the platform initiates the abrasive action on the test specimen.

TEST RESULTS

| | |
|-------------------------|-------------|
| ABRASION WHEEL | H-18 |
| LOAD APPLIED | 1,000 Grams |
| NUMBER OF CYCLES | 1,500 |

| | |
|------------------------|--------------------|
| ORIGINAL WEIGHT | 116.24 Grams |
| FINAL WEIGHT | 116.14 Grams |
| WEIGHT LOSS | 0.10 Grams (0.09%) |
| THICKNESS LOSS | 0.004 Inch |

***NOTE: Test sample was abraded until the color layer was visibly affected. This was considered the end point at 1,500 cycles.**

APPROVED BY: *Gary Osbourn*



This facility is accredited by the National Voluntary Laboratory Accreditation Program for the specific scope of accreditation under Lab Code 100297. This accreditation does not constitute an endorsement, certification, or approval by NIST or any agency of the United States Government for the product tested. This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical or similar products. This report, or the name of Professional Testing Laboratory, Inc. shall not be used under any circumstance in advertising to the general public.





TEST REPORT

DATE: 03-31-2023

Page 4 of 4


TEST NUMBER: 0295655

| | |
|---------------|-------------|
| CLIENT | Lions Floor |
|---------------|-------------|

| | |
|------------------------------|--|
| TEST METHOD CONDUCTED | ASTM D4060 Standard Test Method for Abrasion Resistance of Organic Coatings by the Taber Abraser |
|------------------------------|--|



| DESCRIPTION OF TEST SAMPLE | |
|----------------------------|-------------------|
| IDENTIFICATION | Comfort Heights |
| COLOR | Country Aura |
| ROLL NUMBER | SKU: LI-CH07 |
| CONSTRUCTION | Laminate Flooring |



APPROVED BY: *Gary Asbury*



This facility is accredited by the National Voluntary Laboratory Accreditation Program for the specific scope of accreditation under Lab Code 100297. This accreditation does not constitute an endorsement, certification, or approval by NIST or any agency of the United States Government for the product tested. This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical or similar products. This report, or the name of Professional Testing Laboratory, Inc. shall not be used under any circumstance in advertising to the general public.

