

### **TEST REPORT**

DATE: 03-23-2023	Page 1 of 2	<b>TEST NUMBER</b> : 0295655
CLIENT	Lions Floor	
TEST METHOD CONDUCTED	ISO 24337 Laminate Floor Coverings Geometrical Characteristics	- Determination of

# 

DESCRIPTION OF TEST SAMPLE		
IDENTIFICATION	Comfort Heights	
COLOR	Country Aura	
ROLL NUMBER	sku: LI-Ch07	
CONSTRUCTION	Laminate Flooring	

#### **GENERAL PRINCIPLE**

The submitted goods were measured to determine geometrical values for size, squareness, straightness, height deviations, and gapping when applied together. All values listed are in mm.


#### TEST RESULTS

CHARACTERISTIC			VALUE (mm)					
Thickness			11.775					
Length			1515.313					
Width			235.224					
Straightness					0.042			
Squareness (out of square)		Max:	0.158		Avg:	0.064		
Openings Betwee	en Elem	ents	Max:	0.167		Avg:	0.088	
Height Difference Between Elements		Max:	0.132		Avg:	0.075		
Width Flatness	Max:	0.190	0.08	1%	Avg	0.157	0.067%	Concave
Length Flatness	Max:	0.412	0.02	7%	Avg	0.331	0.022%	Concave

Lary atlenry APPROVED BY:

This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical of similar products. This report, or the name of Professional Testing Laboratory Inc. shall not be used under any circumstance in advertising to the general public.

Fax: 706-226-6787



## **TEST REPORT**

DATE: 03-23-2023	Page 2 of 2	<b>TEST NUMBER</b> : 0295655
CLIENT	Lions Floor	
	ISO 24337 Laminate Floor Covering	s - Determination of
TEST METHOD CONDUCTED	Geometrical Characteristics	

DESCRIPTION OF TEST SAMPLE		
IDENTIFICATION	Comfort Heights	
COLOR	Country Aura	
ROLL NUMBER	SKU: LI-CH07	
CONSTRUCTION	Laminate Flooring	



#### APPROVED BY:

Lang atluny

This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical of similar products. This report, or the name of Professional Testing Laboratory Inc. shall not be used under any circumstance in advertising to the general public.

714 Glenwood Place

Dalton, GA 30721

Phone: 706-226-3283

Fax: 706-226-6787

email: protest@optilink.us