

TEST REPORT

CLIENT	Lions Floor
--------	-------------

TEST METHOD CONDUCTED	ASTM D903 Standard Test Method for Peel or Stripping Strength
	of Adhesive Bonds



DESCRIPTION OF TEST SAMPLE	
IDENTIFICATION	District: 2mm/6mil
COLOR	Carmel
ROLL NUMBER	SKU: LI-DT07
CONSTRUCTION	LVP

GENERAL PRINCIPLE

This test method covers the determination of the comparative peel or stripping characteristics of adhesive bonds when tested on a one inch wide specimen after being applied for 10 days and conditioned in laboratory conditions of 70° F and 50% relative humidity. Samples were tested at 6.0 inches per minute cross head speed.

TEST RESULTS

SPECIMEN 1	6.2 Lbs./Inch
SPECIMEN 2	6.1 Lbs./Inch
SPECIMEN 3	5.9 Lbs./Inch
SPECIMEN 4	6.3 Lbs./Inch
SPECIMEN 5	6.5 Lbs./Inch
SPECIMEN 6	7.1 Lbs./Inch
SPECIMEN 7	6.8 Lbs./Inch
SPECIMEN 8	6.7 Lbs./Inch
SPECIMEN 9	6.5 Lbs./Inch
SPECIMEN 10	6.2 Lbs./Inch
AVERAGE	6.4 Lbs./Inch

APPROVED BY:

Hay afluny

This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical of similar products. This report, or the name of Professional Testing Laboratory Inc. shall not be used under any circumstance in advertising to the general public.

714 Glenwood Place Dalton, GA 30721 Phone: 706-226-3283 Fax: 706-226-6787 email: protest@optilink.us



TEST REPORT

CLIENT	Lions Floor
--------	-------------

TEST METHOD CONDUCTED	ASTM D903 Standard Test Method for Peel or Stripping Strength
	of Adhesive Bonds



DESCRIPTION OF TEST SAMPLE	
IDENTIFICATION	District: 2mm/6mil
COLOR	Carmel
ROLL NUMBER	SKU: LI-DT07
CONSTRUCTION	LVP



APPROVED BY:

Lang aslung

This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical of similar products. This report, or the name of Professional Testing Laboratory Inc. shall not be used under any circumstance in advertising to the general public.

714 Glernwood Place Dalton, GA 30721 Phone: 706-226-3283 Fax: 706-226-6787 email: protest@optilink.us