

TEST REPORT

DATE: 02-26-2021 Page 1 of 1 **TEST NUMBER: 0274334**

CLIENT Lions Floor

TEST METHOD CONDUCTED	ISO	24337	Laminate	Floor	Coverings	-	Determination	of
IESI MEIHOD CONDUCTED	Geometrical Characteristics							



DESCRIPTION OF TEST SAMPLE					
IDENTIFICATION	Lions Floor Grande Collection				
CONSTRUCTION	SPC				
BACKING	EVA				

GENERAL PRINCIPLE

The submitted goods were measured to determine geometrical values for size, squareness, straightness, height deviations, and gapping when applied together. All values listed are in mm.

TEST RESULTS

CHARACTERISTIC	VALUE (mm)
Width Flatness	Max: 0.143 (0.079%) / Avg: 0.108 (0.060%) - Concave
Length Flatness	Max: 0.471 (0.039%) / Avg: 0.314 (0.026%) - Concave
Openings Between Elements	Max: 0.124 / Avg: 0.082
Height Difference Between Elements	Max: 0.136 / Avg: 0.093

APPROVED BY:

Lang asleny This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical of similar products. This

Dalton, GA 30721 Phone: 706-226-3283 Fax: 706-226-6787 714 Glenwood Place email: protest@optilink.us

report, or the name of Professional Testing Laboratory Inc. shall not be used under any circumstance in advertising to the general public.