

TEST REPORT

| DATE: 08-30-2022 | Page 1 of 1 | TEST NUMBER : 0288981 |
|-----------------------|---|--------------------------------|
| CLIENT | Lions Floor | |
| | | |
| TEST METHOD CONDUCTED | ASTM D903 Standard Test Method of Adhesive Bonds | for Peel or Stripping Strength |

| DESCRIPTION OF TEST SAMPLE | | |
|----------------------------|---------------------------------------|--|
| IDENTIFICATION | Lions Floor Indoor Delight collection | |
| COLOR | LI-ID01 Country Breeze | |
| CONSTRUCTION | SPC | |
| BACKING | EVA | |

GENERAL PRINCIPLE

This test method covers the determination of the comparative peel or stripping characteristics of adhesive bonds when tested on a one inch wide specimen after being applied for 10 days and conditioned in laboratory conditions of 70° F and 50% relative humidity. Samples were tested at 6.0 inches per minute cross head speed.

TEST RESULTS

| SPECIMEN 1 | 8.8 Lbs./Inch |
|-------------|---------------|
| SPECIMEN 2 | 9.2 Lbs./Inch |
| SPECIMEN 3 | 9.1 Lbs./Inch |
| SPECIMEN 4 | 8.9 Lbs./Inch |
| SPECIMEN 5 | 9.0 Lbs./Inch |
| SPECIMEN 6 | 9.1 Lbs./Inch |
| SPECIMEN 7 | 9.2 Lbs./Inch |
| SPECIMEN 8 | 8.7 Lbs./Inch |
| SPECIMEN 9 | 8.6 Lbs./Inch |
| SPECIMEN 10 | 9.0 Lbs./Inch |
| AVERAGE | 9.0 Lbs./Inch |

Lang athury APPROVED BY:

This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical of similar products. This report, or the name of Professional Testing Laboratory Inc. shall not be used under any circumstance in advertising to the general public.