



TEST REPORT

DATE: 09-06-2022

Page 1 of 1

TEST NUMBER: 0289067

CLIENT	Lions Floor
---------------	-------------

TEST METHOD CONDUCTED	ASTM F1914 ASTM F3261 Test Method for Short-Term Indentation and Residual Indentation of Resilient Floor Covering
------------------------------	---



DESCRIPTION OF TEST SAMPLE	
IDENTIFICATION	Lions Floor Lone Star Spirit Collection (Packaged in Red/White/Blue Boxes)
COLOR	LI-TS106 Saddle Brownie
CONSTRUCTION	SPC
BACKING	EVA

RESIDUAL INDENTATION PROCEDURE

A test sample is loaded with 75 lbs. on a presser foot .250 inches in diameter for 15 minutes. After 60 minutes of recovery time the indentation is measured again and compared to the original thickness of the sample.

TEST RESULTS

RESIDUAL INDENTATION AT 75 Lbs.	0.001 inch
--	------------

SURFACE INTEGRITY INDENTATION PROCEDURE

A test sample is loaded with 140 lbs. on a presser foot .178 inches in diameter for 10 minutes. The indentation is immediately inspected for surface integrity.

TEST RESULTS

SURFACE INTEGRITY	No puncture through wear layer/décor into rigid core.
--------------------------	---

APPROVED BY:

This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical of similar products. This report, or the name of Professional Testing Laboratory Inc. shall not be used under any circumstance in advertising to the general public.