

## **TEST REPORT**

DATE: 09-06-2022 Page 1 c	of 1 TEST NUMBER: 0289066
---------------------------	---------------------------

**CLIENT** Lions Floor

TEST METHOD CONDUCTED	ASTM D2047 James Machine - Coefficient of Friction on Flooring	
IEST METHOD CONDUCTED	Material	



DESCRIPTION OF TEST SAMPLE				
IDENTIFICATION	Lions Floor Natural Essence Plus Collection (Packaged in Green/White/Blue Boxes)			
COLOR	LI-NE208 Tresor			
CONSTRUCTION	SPC			
BACKING	EVA			

## **GENERAL PRINCIPLE**

This test was used to measure the relative static coefficient of friction by using the James Machine.

## **TEST RESULTS**

TEST ENVIRONMENT	69° F 50% Relative Humidity

Sensor Materials	Dry
Standard Neolite	1.02

APPROVED BY:

Lang atluny

This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical of similar products. This report, or the name of Professional Testing Laboratory Inc. shall not be used under any circumstance in advertising to the general public.

714 Glenwood Place Dalton, GA 30721 Phone: 706-226-3283 Fax: 706-226-6787 email: protest@optilink.us