



TEST REPORT

DATE: 09-06-2022

Page 1 of 1

TEST NUMBER: 0289068

CLIENT	Lions Floor
---------------	-------------

TEST METHOD CONDUCTED	ASTM D903 Standard Test Method for Peel or Stripping Strength of Adhesive Bonds
------------------------------	---



DESCRIPTION OF TEST SAMPLE	
IDENTIFICATION	Lions Floor Lone Star Spirit XL Collection (Packaged in Red/White/Blue Boxes)
COLOR	LI-TS206 Shangri La
CONSTRUCTION	SPC
BACKING	EVA

GENERAL PRINCIPLE

This test method covers the determination of the comparative peel or stripping characteristics of adhesive bonds when tested on a one-inch wide specimen after being applied for 10 days and conditioned in laboratory conditions of 70° F and 50% relative humidity. Samples were tested at 6.0 inches per minute cross head speed.

TEST RESULTS

SPECIMEN 1	9.6 Lbs./Inch
SPECIMEN 2	9.6 Lbs./Inch
SPECIMEN 3	9.5 Lbs./Inch
SPECIMEN 4	9.3 Lbs./Inch
SPECIMEN 5	9.2 Lbs./Inch
SPECIMEN 6	9.2 Lbs./Inch
SPECIMEN 7	9.4 Lbs./Inch
SPECIMEN 8	9.3 Lbs./Inch
SPECIMEN 9	9.2 Lbs./Inch
SPECIMEN 10	9.5 Lbs./Inch
AVERAGE	9.4 Lbs./Inch

APPROVED BY:

This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical or similar products. This report, or the name of Professional Testing Laboratory Inc. shall not be used under any circumstance in advertising to the general public.