

Lions Floor

TEST REPORT

SCOPE OF WORK

WPC floors

REPORT NUMBER

240726001SHF-002-R1

TEST DATE(S)

2024-07-26 - 2024-08-13

ORIGINAL ISSUE DATE

2024-08-22

REVISED DATE

2024-08-29

PAGES


17

DOCUMENT CONTROL NUMBER

LFT-APAC-SHF-OP-10k(February 1, 2024)

© 2024 INTERTEK

Intertek Testing Services Shenzhen Ltd. Shanghai Fengxian Branch



Test Report

Statement

- 1.This report is invalid without company's special seal for testing on the assigned page.
- 2.This report is invalid without an authorized person's signature.
- 3.This report is invalid if altered.
- 4.Only the Client is authorized to permit copying or distribution of this report and then only in its entirety. Don't copy this report in partial without any official approval in written by our company. This report is invalid without re-stamping the special seal for testing in copying report.
- 5.This report is for the exclusive use of Intertek's Client and is provided pursuant to the agreement between Intertek and its Client. Intertek's responsibility and liability are limited to the terms and conditions of the agreement. Intertek assumes no liability to any party, other than to the Client in accordance with the agreement, for any loss, expense or damage occasioned by the use of this report. Any use of the Intertek name or one of its marks for the sale or advertisement of the tested material, product or service must first be approved in writing by Intertek. The observations and test results in this report are relevant only to the sample(s) tested. This report by itself does not imply that the material, product, or service is or has ever been under an Intertek certification program.
- 6.Except for the obligation, responsibility and liability (if any) for the appropriateness and professionalism of afore-mentioned testing itself within the scope and amount of the testing fee received, Intertek does not and will not accept any other obligation or liability.
- 7.If the Client has any questions about the test results, Intertek B&C should be informed within the storage period of the samples. The sample storage period ends 5 working days after the official report issue date. Samples of certification program are retained for the period required by the certification rules. The samples storage period shall be calculated according to the issue date of the original report in the case of quoting results and modifying reports.
- 8.Intertek B&C will service this report for the entire test record retention period. The test record retention period ends 6 years after this report original issue date. The test record retention period for certification program is 10 years. Test records and other pertinent project documentation will be retained for the entire test record retention period.
- 9.The report was digital signed by Shang Hai, Intertek Group plc, please using Adobe Acrobat Reader to verify the authenticity.

Test Report

Original Issue Date: 2024-08-22 Revised Date: 2024-08-29 Intertek Report No. 240726001SHF-002-R1

Applicant: Lions Floor

Address: 7300 somerset blvd, paramount, CA 90723

Attn: Jerry Guo

Test Type: Performance test, samples provided by the applicant.

Product Information

Product Name	Model	Specification
WPC floors	Seaside Summit	2100*239*8+2mm
Sample ID	Sample Amount	Sample Received Date
S240726001SHF.018~032	48 pieces	2024-05-31
Sample Description		
2100*239*8+2mm		


Test Methods And Standards

Test Standard	With reference to ASTM D2047-17 and client's requirement, ASTM F3261-20 section 8.1, 8.3, 8.5, 8.6, 8.7, ASTM F1514-19, ASTM F1515-21, ASTM F1914-18(2023), ISO 23999:2021, ASTM F387-17(2022), ASTM F410-08(2022), ANSI A326.3-2021, ASTM D4060-19, ASTM D903-98(2017), ASTM F970-22, ISO 24334:2019, ISO 4918:2016/Amd.1:2018
Specification Standard	/
Test Conclusion	The samples were tested according to the above standards, and the results are shown in the following page.

Note:

1.This report does not involve sampling. The report only reflects conformity of the tested items of the samples provided by the testing applicant. Representativeness and authenticity of the submitted samples are responsibilities of the testing applicant.

Report Authorized


Name: Flora Fan Name: Daniel Zhang
Title: Reviewer Title: Project Engineer

Test Report

Original Issue Date: 2024-08-22

Revised Date: 2024-08-29

Intertek Report No. 240726001SHF-002-R1

Test Items, Method and Results:

Test Item	Test Method	Test Result
Static Coefficient of Friction (Standard Leather)	With reference to ASTM D2047-17 and client's requirement	Dry: 0.58 Wet ¹ : 1.00

Note:

1. ASTM D2047 does not require test under wet condition, test result is only for reference as per the client's requirement.



Test Report

Original Issue Date: 2024-08-22

Revised Date: 2024-08-29

Intertek Report No. 240726001SHF-002-R1

Test Items, Method and Results:

Test Item: Resistance to heat

Test Method: ASTM F3261-20 section 8.5 and ASTM F1514-19

Conditioning: Condition the test specimens at $(23 \pm 2)^\circ\text{C}$ and $(50 \pm 5)\%$ relative humidity for at least 24h

Test Condition:

Temperature: 70 °C


Exposure time: 7 days

Spectrophotometer: Under D65 standard light source, 10° observer

Test Result:

Specimen	ΔE^*	Average ΔE^*
1	1.51	1.40
2	1.35	
3	1.34	

Test Photo:



After exposure

Test Report

Original Issue Date: 2024-08-22

Revised Date: 2024-08-29

Intertek Report No. 240726001SHF-002-R1

Test Items, Method and Results:

Test Item: Resistance to light

Test Method: ASTM F3261-20 section 8.6 and ASTM F1515-21

Conditioning: Condition the test specimens at $(23 \pm 2)^\circ\text{C}$ and $(50 \pm 5)\%$ relative humidity for at least 24h


Test Condition:

Light source: Xenon-arc lamps
Irradiance: 0.30 $\text{W}/(\text{m}^2 \cdot \text{nm})$ at 340nm
Black-panel temperature: 63 ± 2 $^\circ\text{C}$
Relative humidity: 50 ± 10 %
Exposure time: 300 h
Spectrophotometer: Under D65 standard light source, 10° observer

Test Result:

Specimen	ΔE^*	Average ΔE^*
1	1.06	1.60
2	2.00	
3	1.75	

Test Photo:



After exposure

Test Report

Original Issue Date: 2024-08-22

Revised Date: 2024-08-29

Intertek Report No. 240726001SHF-002-R1

Test Items, Method and Results:

Test Item: Residual indentation

Test Method: ASTM F3261-20 section 8.1 and ASTM F1914-18(2023)

Conditioning: Condition the test specimens at $(23 \pm 2)^{\circ}\text{C}$ and $(50 \pm 5)\%$ relative humidity for at least 24h

Test Condition:

Indenter: Steel cylindrical foot

Indenter diameter: 6.35 mm

Total load applied: 34 kg

Indentation time: 15 min

Recovery time: 60 min

Test Result:

Residual Indentation	Result (mm)
Specimen 1	0.03
Specimen 2	0.03
Specimen 3	0.03
Average value	0.03
Max. value	0.03

Test Report

Original Issue Date: 2024-08-22

Revised Date: 2024-08-29

Intertek Report No. 240726001SHF-002-R1

Test Items, Method and Results:

Test Item: Dimensional stability and curling

Test Method: ASTM F3261-20 section 8.3 and ISO 23999:2021

Conditioning:

Temperature: 23 °C

Relative humidity: 50 %

Duration: 24 h

Measure the initial length and curling

Test Condition:

Temperature: 70 °C

Duration: 6 h

Reconditioning:

Temperature: 23 °C

Relative humidity: 50 %

Duration: 24 h

Measure the final length and curling

Test Result:

Specimen	Dimensional stability (%)		Curling (in.)
	Length direction/Machine direction	Width direction/Across machine direction	
1	-0.08	0.02	0.047
2	-0.10	0.01	0.023
3	-0.13	0.01	0.013
Average	-0.10	0.01	0.028
Max.	-0.13	0.02	0.047

Note:

1. Dimensional stability = (final length - initial length)×100/initial length

Express the average value to the nearest 0.05%

A negative value indicates shrinkage and a positive value indicates growth.

2. Curling = final curling - initial curling

Express the average value to the nearest 0.5mm

Upward curling is expressed as a positive value and downward curling (sometimes referred to as doming) is expressed as a negative value.

Test Report

Original Issue Date: 2024-08-22

Revised Date: 2024-08-29

Intertek Report No. 240726001SHF-002-R1

Test Items, Method and Results:

Test Item: Thickness

Test Method: ASTM F387-17(2022)

Conditioning: Condition the test specimens at $(23 \pm 2)^{\circ}\text{C}$ and $(50 \pm 5)\%$ relative humidity for at least 24h

Test Condition:

Foot diameter of thickness gage: 6.35 mm

Mass applied: 28 g

Product with foam back layer: Yes

Test Result:

Nominal value: 10.0 mm

Average value: 10.14 mm

Tolerance: 0.14 mm

Max. value: 10.16 mm

Min. value: 10.13 mm

Test Report

Original Issue Date: 2024-08-22

Revised Date: 2024-08-29

Intertek Report No. 240726001SHF-002-R1

Test Items, Method and Results:

Test Item: Wear layer thickness

Test Method: ASTM F410-08(2022)

Conditioning: Condition the test specimens at $(23 \pm 2)^{\circ}\text{C}$ and $(50 \pm 5)\%$ relative humidity for at least 24h

Test Result:

Nominal value: 0.70 mm

Average value: 0.70 mm

Max. value: 0.71 mm

Min. value: 0.69 mm

Test Report

Original Issue Date: 2024-08-22

Revised Date: 2024-08-29

Intertek Report No. 240726001SHF-002-R1

Test Items, Method and Results:

Test Item: Dynamic Coefficient of Friction

Test Method: ANSI A326.3-2021

Test Results:

Test Items	Test Method	Test Results	
Dynamic Coefficient of Friction	ANSI A326.3-2021	Dry condition:	0.51
		Wet condition:	0.47

Note:

1. Test item is subcontracted on accreditation by CNAS L1978.

Test Report

Original Issue Date: 2024-08-22

Revised Date: 2024-08-29

Intertek Report No. 240726001SHF-002-R1

Test Items, Method and Results:

Test Item: Abrasion/Wear resistance

Test Method: ASTM D4060-19

Conditioning: Condition the test specimens at (23±2)°C and (50±5)% relative humidity for at least 24h

Test Condition:

Rotation frequency: 60 r/min

Abrasive wheels: CS-17

Load on each wheel: 1000 g

Test revolutions: 1000 r

Test Result:

Parameter	Specimen 1	Specimen 2	Specimen 3
Mass/Weight loss, (mg)	131.9	140.1	152.1
Average value, (mg)	141.4		

Note:

1. Abbreviation "r" = revolutions/cycles
2. Test conditions were specified by client.

Test Report

Original Issue Date: 2024-08-22

Revised Date: 2024-08-29

Intertek Report No. 240726001SHF-002-R1

Test Items, Method and Results:

Test Item: Peel Strength

Test Method: ASTM D903-98(2017)

Conditioning: Condition the test specimens at (23±1)°C and (50±2)% relative humidity for at least 7days

Test Condition:

Test Speed: 152.4 mm/min

Test Result:

Test Items	Test Results
Peel Strength	Length direction/Machine direction mean value: 0.44kg/mm
	Width direction/Across machine direction mean value: 0.45kg/mm

Note:

1. Finish product was provided by client, peel strength of wear layer and substrate was tested.

Test Report

Original Issue Date: 2024-08-22

Revised Date: 2024-08-29

Intertek Report No. 240726001SHF-002-R1

Test Items, Method and Results:

Test Item: Static load resistance

Test Method: ASTM F3261-20 section 8.7 and ASTM F970-22

Conditioning: Condition the test specimens at $(23 \pm 2)^{\circ}\text{C}$ and $(50 \pm 5)\%$ relative humidity for at least 24h

Test Condition:

Indenter diameter: 28.6 mm

Total load applied: 250 lb / 250 psi

Indentation time: 24 h

Recovery time: 24 h

Test Result:

Residual Indentation	Result (mm)
Specimen 1	0.35
Specimen 2	0.46
Specimen 3	0.49
Average value	0.43
Max. value	0.49

Test Report

Original Issue Date: 2024-08-22

Revised Date: 2024-08-29

Intertek Report No. 240726001SHF-002-R1

Test Items, Method and Results:

Test Item: Locking Strength

Test Method: ISO 24334:2019

Conditioning: Condition the test specimens at (23±2)°C and (50±5)% relative humidity to constant mass

Test Condition: Test speed 0.5 mm/min

Test Result:

Longitudinal joint

Parameter	Average Result
Maximum locking strength F_{max} (N)	1067
Specific locking strength (kN/m)	5.1
Locking strength at 0.2 mm joint opening $F_{0.2}$ (N)	529
Specific locking strength at 0.2 mm joint opening (kN/m)	2.5

Transverse joint

Parameter	Average Result
Maximum locking strength F_{max} (N)	1335
Specific locking strength (kN/m)	6.4
Locking strength at 0.2 mm joint opening $F_{0.2}$ (N)	802
Specific locking strength at 0.2 mm joint opening (kN/m)	3.8

Test Report

Original Issue Date: 2024-08-22

Revised Date: 2024-08-29

Intertek Report No. 240726001SHF-002-R1

Test Items, Method and Results:

Test Item: Castor chair test

Test Method: ISO 4918:2016/Amd.1:2018

Conditioning: Condition the test specimens at (23 ± 2)°C and (50 ± 5)% relative humidity for at least 24h

Test Condition: At a temperature range of 18°C to 25 °C

Load mass: 90 kg

Test castors: Type W

Speed of rotating platform: 20 r/min

Speed of castor assembly: 50 r/min

Total test revolutions: 25000 r

Mounting of the specimen: Floating installation with click joints

Test Result:

Type of damage	Observation (Yes/No)	Verdict
Delamination	No	Pass
Opening of joints	No	
Surface damage	No	
Crazing	No	
Maximum opening	0.02mm	No requirement Report the result
Maximum height differences	0.08mm	

Test Photo:



After test

Test Report

Original Issue Date: 2024-08-22

Revised Date: 2024-08-29

Intertek Report No. 240726001SHF-002-R1

Appendix A: Sample Received Photo



Revision:

NO.	Date	Changes
240726001SHF-002	2024-08-22	First issue
240726001SHF-002-R1	2024-08-29	Revise typo on page 3

Note: Since the issue date of 240726001SHF-002-R1 report, the original report 240726001SHF-002 was cancelled at the same time.